

Standard Available in forms :

- ASTM A182/ ASME SA182 Stainless Steel Pipe Fittings
- ASTM A213 / ASME SA213 Seamless Stainless Steel Pipes
- ASTM A240/ ASME SA240 Stainless Steels Sheets / Plates
- ASTM A249/ ASME SA249 Stainless Steel Welded Tubes
- ASTM A269/ ASME SA269 Stainless Steel Tubes
- ASTM A270/ ASME SA270 Stainless Steel Sanitary Tubes
- ASTM A312/ ASME SA312 Stainless Steel Pipes
- ASTM A403/ ASME SA403 Stainless Steel Pipe Fittings
- ASTM A554/ ASME SA554 Stainless Steel Welded Tubes
- ASTM A731/ ASME SA731 Stainless Steel Pipes
- ASTM A789/ ASME SA789 Stainless Steel Tubes
- ASTM A790/ ASME SA790 Stainless Steel Pipes
- ASTM A791/ ASME SA791 Stainless Steel Tubes

Products Available in forms :

- SS 301, WNR 1.4310, UNS S30100, AISI 301 Plates
- SS 301, WNR 1.4310, UNS S30100, AISI 301 Pipes
- SS 301, WNR 1.4310, UNS S30100, AISI 301 Round Bar
- SS 301, WNR 1.4310, UNS S30100, AISI 301 Tube
- SS 301, WNR 1.4310, UNS S30100, AISI 301 Flanges
- SS 301, WNR 1.4310, UNS S30100, AISI 301 Wire
- SS 301, WNR 1.4310, UNS S30100, AISI 301 Fittings

Corrosion Resistance

- The resistance to corrosion offered by stainless steel grade 301 is similar to that offered by 304.
- This grade exhibits good resistance to corrosion in mildly corrosive environments at ambient temperatures.

Heat Resistance

- Grade 301 exhibits good oxidation resistance for intermittent services up to 840°C and for continuous service up to 900°C.

Heat Treatment

- Stainless steel grade 301 is subjected to solution treatment annealing in temperatures ranging from 1010°C to 1120°C followed by rapid cooling.
- For intermediate annealing a low temperature range is chosen. Thermal hardening does not suit this grade of stainless steel.

Cold Working

- Stainless steel grade 301 and low carbon variants of this grade are predominantly used as high strength stainless steel.
- The work hardening rates of these grades are very high, in the range of a 14MPa increase per 1% reduction in area of cold work.
- As a result of this characteristic high strength can be achieved from cold rolling and roll forming operations.
- Through such forming methods strain hardened austenite may be partially transformed to martensite.
- In spite of achieving such high strengths, the residual ductility in the alloy is capable of causing severe cold deformation.
- The alloy is non-magnetic in the annealed condition, but shows strong magnetism when cold worked.

Welding

- Stainless steel grade 301 is suitable for all forms of standard welding methods.
- The use of grade 308L as filler metal is recommended.
- Welded parts in grade 301 must be subjected to annealing in order to attain maximum corrosion resistance.
- For grades 301L and 301LN annealing is not necessary after welding.
- The purpose of welding followed by annealing is to remove the high strength brought about by cold rolling.
- The process of spot welding is used to assemble the cold rolled 301 components; this rapid welding technique does not hamper the overall strength of the component.

Applications

Some of the typical applications of grade 301 stainless steels are listed below:

- Making rail car structural components
- Air frame sections
- Highway trailer components
- Automotive wheel covers
- Wiper blade clips and holders
- Stove element clips
- Screen frames
- Toaster springs
- Curtain walls



**9/A, 9th Floor, Mehta Mehal,
15th Mathew Road, Opera House,
Charni Road, Mumbai - 400 004, India.**

web: www.aesteiron.com

email: info@aesteiron.com

Tel: +91-22-67776700 - 6799 - 6777



© 2019-20. The content on this website is owned by Registrant of domain www.aesteiron.com, Do not copy any content (including images) without prior written consent. Manufacturer, Stockholder, Suppliers, Traders, Wholesaler, Dealer, Distributor, Importer, Exporter, Stockiest of Alloy Steel PipeTubes, Stainless Steel Pipe Tube & Carbon Steel Pipe Tube